

**SPECIFICATIONS FOR CENTRIFUGED NATURAL RUBBER LATEX - THAILAND**

PROPERTIES	I.S.O. SPECIFICATIONS	
	HA	LA
Total Solid Content (% by weight)	61.50 min	61.50 min
Dry Rubber Content (% by weight)	60.00 min	60.00 min
Non-Rubber Solids (%)	2.0 max	2.0 max
Ammonia Content (on total weight) %	0,60 min	0.29 max
Ammonia Content (on water phase) %	-	-
PH Value (at 25 *c)	-	-
KOH Number	1.0 max	1.0 max
Volatile Fatty Acid Number (VFA)	0.20 max	0.20 max
Mechanical Stability Time @ 55% TS., Sec.	650 min	650 min
Magnesium Content (on Solids), WM	-	-
Odour of Latex	-	-
Colour of Latex	-	-
Colour of Film	-	-

All tests performed according to the relevant I.S.O. 2004-1979E Specification