

KER[®] 1904

High-Styrene Rubber - HSR

Technical Data Sheet

Date of edition: 30/09/2009

Edition: 2

Approved by: Product Manager – Zdeněk Herber

Previous editions of this document have lost their validity

Page 1 of 1

CHARACTERISTICS

KER[®] 1904 is a grade of high-styrene rubber. It is produced by mixing of styrene-butadiene latex and high styrene resin in adequate proportion. It is coagulated by a system of acid and synthetic coagulant, is stabilized with a non-staining antioxidant and contains abt. 68% of bonded styrene.

GENERAL REQUIREMENTS

HSR is packed into polyethylene bags 25.0 ± 0.5 kg. Presence of any mechanical impurities is not permitted.

TECHNICAL PARAMETERS

RUBBER TECHNICAL PARAMETERS

Parameters
Volatile matters
Total ash
Organic acids
Soaps

Test methods
ASTM D5668
ASTM D5667
ASTM D5774
ASTM D5774

Guaranteed values of relevant parameters are specified in the sales contract.

To each shipping lot/delivery, a certificate of analysis is determined during release certificate is each time agreed

with the time agreed upon in the sales contract. The properties of the product is covered by the quality certificate.

PACKAGING

KER[®] 1904 has a form of granules, packed onto 1.2 t wooden pallets of

25.0 ± 0.5 kg each, then laid

TRANSPORTATION

KER[®] is typically transported in covered road trucks, in covered railway carriages and in standard shipping containers, in rail tank cars or road tankers. KER[®] 1904 is not a dangerous material to transport.

STORAGE

Product should be stored in sheltered conditions away from direct sunlight, at least 2 meters away from radiant heating elements and the temperature should not exceed 30°C. The guaranteed shelf life for KER[®] under the above-mentioned conditions is twelve (12) months from the date of production.

APPLICATION

KER[®] 1904 is used for production of floor finishes, cables, toys and micro porous rubber for footwear industry.

This document is of an informative character. The information given herein is based on the present state of our knowledge and experience. It makes neither product properties nor qualitative parameters guarantee and cannot be used as a basis of any claims. The information provided cannot be used for any mixtures with any other substances. Product should be transported, stored and used in accordance with valid regulations and good occupational hygiene practice.

Making use of the information as well as product application is beyond the producer control and determination of the safe conditions of use is the sole responsibility of a customer.